

TECHNICAL DATA SHEET

1. PRODUCT CLASS

CPL plastic laminate.

2. DESCRIPTION

SILK laminate is obtained by laminating a special acrylic film with various layers of phenolic free support according to the required thickness. Thanks to Electron Beam Curing technology (EBC), the acrylic surface of SILK against extraordinary properties such as: anti fingerprint, high scratch resistance, light fastness, no bacterial proliferation, high resistance to solvents and chemical reagents. Any small traces of grease can be eliminated very easily thanks to the oleophobic properties of SILK Laminate. These technical features, joined with its Soft and Supermatt surfaces, make SILK laminate a cutting-edge product in the world of interior design appreciated by architects and designers. Last but not least, SILK laminate is a Phenol Free product, an additional choice for environment protections and consumers health confirming Neodecortech spa commitment toward the green chemistry.

3. PROPERTIES

- a) Surface with higher chemical and mechanical resistance
- b) Possibility to produce all the range of thicknesses from 0,4 to 1,8 mm.
- c) Applicability with all kinds of plants used in the lamination business (however the customer is recommended to test in advance).

4. RECOMMENDATIONS

- a) SILK laminate doesn't have postforming property; it therefore is **not post-formable**.
- b) When handling or moving decorative laminates it is important that the sheets be lifted above adjacent sheets to avoid damage that can occur if the sheets are pulled or slid against each other. For SILK laminate, it is advisable to require the application of a protective film.
- c) The product is not waterproof so it must be stored in places that are not in direct and constant contact with moisture; the same applies to laminate-coated items.
- d) It is recommended to use glues that have the necessary moisture resistance, preferring polyurethane glue (PUR).
- e) Before bonding, both laminates and substrates must be cleaned and free from any traces of dust, grease, particles or other impurities that could cause defects, bubbles or stains on the surface of the finished panel.
- f) Pre-conditioning the laminate at temperature and humidity conditions of the place where the gluing process will be performed. However, it is not advisable to glue the laminate if the temperature is < 15 ° C.

5. APPLICATIONS

- a) SILK laminate is a product particularly suitable for coating plain, vertical and horizontal surfaces, it can be applied on chipboard, MDF and plywood using all standard gluing processes.
- b) Silk laminate is suitable for the use in the naval field certified by LAPI S.p.A.; certificates 0987/MED-B/546 (form B) and 0987/MED-D/466 (form D).
- c) SILK laminate can be applied with standard glue processes used in the lamination business. However, the customer is recommended to test in advance.

6. SIZES

Supplied in sheets of size: width 1.320 mm and length from 2.000 to 4.200 mm.

7. TECHNICAL CHARACTERISTICS

The technical characteristics are shown in the table below.

8. PACKAGING AND STORAGE

Please refer to the "Packaging and Storage chart" uploaded on our website for complete details.

9. NOTES

Information contained in this document are based on our current knowledge and experience. However, they cannot be considered exhaustive, but purely indicative. It is recommended to test the products at your premises in advance and to report any non-conformities before proceeding with the production. Neodecortech S.p.A. cannot be considered liable for any damage deriving from the use of the abovementioned product.

TEXTE SILK LAMINATES

SILK laminate has been produced according to EN 438-2:2019 only in those cases where it is specifically declared: see table below. Other areas of this standard not expressly referred to, are not applicable/guaranteed.

PROPERTY	Test method	Property or attribute	Unit / Rating (max or min)	VALUES
SURFACES QUALITY				
Surface Quality	EN 438-3	Spots, dirt and similar surface defects	mm ² /m ²	≤ 1
		Fibers, hairs and scratches	mm/m ²	≤ 10
DIMENSIONAL TOLERANCES				
Dimensional Tolerances	EN 438-2.5	Thickness tolerance	mm	0,5 ≤ t ≤ 1,0 ± 0,10
			mm	1,0 ≤ t ≤ 2,0 ± 0,15
	EN 438-2.6	Length and width	mm	+ 10 - 0
	EN 438-2.7	Straightness of edges	mm/m	1,5
	EN 438-2.8	Squareness	mm/m	1,5
EN 438-2.9	Flatness ⁽¹⁾	mm/m	60	
GENERAL PROPERTIES				
Resistance to surface wear	EN 438-2.10	Initial Point	Revolutions	200
Resistance to water vapor	EN 438-2.14	Appearance - Gloss Finish	Rating (min)	3
Resistance to dry heat (180°C)	EN 438-2.16	Appearance - Gloss Finish	Rating (min)	4
Resistance to wet heat (100 °C)	EN 438-2.18	Appearance - Gloss Finish	Rating (min)	4
Dimensional stability at elevated temperature	EN 438-2.17	Cumulative dimensional change	Longitudinal %	0,60
		Cumulative dimensional change	Transversal %	1,20
Resistance to impact with small diameter ball	EN 438-2.20	Spring Force	N(min)	15
Resistance to scratching	EN 438-2.25	Appearance	Rating (min)	3
Resistance to staining	EN 438-2.26	Appearance - Group 1&2	Rating (min)	5
		Appearance - Group 3	Rating (min)	4

⁽¹⁾ Provided that the laminate is stored in the manner and conditions recommended by the manufacturer.

SPECIFIC USE

The Thin top MED version is suitable for use in the naval field as certified by LAPI SpA with reference to PRODUCTION QUALITY ASSURANCE CERTIFICATE (Module D) N° 0987/MED-D/936 and EC TYPE-EXAMINATION CERTIFICATE (Module B) N° 0987/MED-B/809.